

## **IN THE SPECIFICATION**

*Please amend the second full paragraph on page 2 as follows:*

-- The positive electrode current collector for a manganese dry battery of the present invention comprises a carbon rod, and either one of a paraffin wax containing hydrocarbon whose molecular weight is 300 to 500 and a microcrystalline wax containing hydrocarbon whose molecular weight is 500 to 800, which is impregnated into the carbon rod, is characterized in that the endothermic amount of the paraffin wax or the microcrystalline wax, which is obtained by differential scanning calorimetry <sup>[[up]]</sup> at 20 to 45°C, is not more than 1.0 J/g.--

*Please amend the second full paragraph on page 4 as follows:*

--The positive electrode current collector for a manganese dry battery of the present invention comprises a carbon rod and either one of a paraffin wax containing hydrocarbon whose molecular weight is 300 to 500 and a microcrystalline wax containing hydrocarbon whose molecular weight is 500 to 800, which is impregnated into the carbon rod, is characterized in that the endothermic amount of the paraffin wax or the microcrystalline wax obtained by differential scanning calorimetry <sup>[[up]]</sup> at 20 to 45°C is not more than 1.0 J/g.--